

## Technical Data Sheet UV Curable Cylinlock<sup>®</sup> 821

October 2019

Page 1 of 2

### Product Description

**Hernon<sup>®</sup> UV Curable Cylinlock<sup>®</sup> 821** is a fast curing, high strength anaerobic adhesive designed to retain and seal cylindrical assemblies. Curing occurs when adhesive is confined between mating surfaces. The cured adhesive is a thermoset plastic suitable for exposure to most solvents and withstands temperatures up to 300°F (149°C). Augments or replaces press fits, set screws, pins and other mechanical retaining methods. Avoids heavy press fits due to rapid cure.

**Cylinlock<sup>®</sup> 821** cures quickly at room temperature without the need for surface activators or heat to join cylindrical assemblies. Fixturing strength develops in five minutes, or within 15 seconds by exposing the edge fillets to high intensity long wavelength UV light (365 nm). Full strength will be reached in 24 hours.

### Typical Properties (Uncured)

Property	Value
Chemical Type	Urethane Methacrylate
Appearance	Yellow- Amber Liquid
Viscosity @ 77°F (25°C), cP	500 to 700
Specific gravity	1.09
Flash point	See SDS

### Typical Properties (Cured)

Property	Value
UV cure time (US1000)	3 - 5 seconds
UV cure time (LED9)	≤ 10 seconds
Temperature Range, °F	-65 to 300

### Typical Curing Performance

#### **Curing Specifications**

Curing occurs when the resin is confined between metallic surfaces. The metal acts as a catalyst for the curing process. Hot air oven heat or induction heat will fully cure these compounds. To ensure proper cure of UV fillets, UV light intensities above 60 milliwatts/cm<sup>2</sup> is recommended.

#### **Fixture Time and Surface Cure**

UV fixture time is defined as the light exposure time required to develop a shear strength of 0.1 N/mm<sup>2</sup>. When curing with sufficient UV light irradiance, exposed material cures dry to the touch in seconds.

### Typical Cured Performance

Compressive Shear Strength,  
Tested at RT, on steel pins and collars according to ASTM D4562.

Cure Conditions	Temperature	Strength, psi
24 Hours	22 °C	≥ 2500

### General Information

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some case these aqueous washes can affect the cue and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

#### **Directions for Use**

For best results, clean all surfaces (external and internal) with a **Hernon<sup>®</sup>** cleaning solvent and allow to dry. If the material is an inactive metal or the cure speed is to slow, apply **Activator 49 or 50** and allow to dry.

**For Slip Fitted Assemblies**, apply adhesive around the leading edge of the pin and the inside of the collar and use a rotating motion during assembly to ensure good coverage.

**For Press Fitted Assemblies**, apply adhesive thoroughly to both bond surfaces and assemble at high press on rates.

**For Shrink Fitted Assemblies** the adhesive should be coated onto the pin, the collar should then be heated to create sufficient clearance for free assembly. Parts should not be disturbed until sufficient handling strength is achieved.

#### **Disassembly and Cleanup**

To aid in disassembly anaerobic compounds can be weakened by heating to at least 500°F (260°C). Once

disassembled, cured adhesive can be removed with **Hernon® Gasket Remover 30**.

**Storage**

**Cylinlock® 821** should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

**Dispensing Equipment**

**Hernon®** offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.