

Mine Bonder 2005

Product Description

Hernon® Mine Bonder 2005 is an anaerobic adhesive sealant which cures rapidly through large gaps with **Hernon® Primer 50**.

Typical Properties

Property	Value
Resin	Methacrylate ester
Appearance	Amber liquid
Viscosity @ 25°C, cP (Spindle 6 at 10 rpm)	22,000-30,000

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.

Typical Curing Performance

Hernon® Mine Bonder 2005 will be gelled in 2- to 4 hours by mixing **Hernon® Primer 50** (6 drops).

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Storage

Mine Bonder 2005 should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.