

Ultrabond 774

Product Description

Hernon[®] Ultrabond[®] 774 is a one component adhesive which cures when exposed to ultraviolet radiation and/or visible light of sufficient intensity.

Typical Applications

Ultrabond[®] 774 has shown excellent adhesion to a wide variety of substrates including glass, many plastics and most metals and exhibits excellent water resistance.

Properties of Uncured Material

Property	Value
Chemical Type	Acrylated Urethane
Appearance	Red Liquid
Specific Gravity @ 25°C	1.07
Viscosity at 25°C, cP spindle 3, 20 rpm	2,000-3,000
Refractive Index, N _D	1.484
Flash Point	See SDS

Typical Properties (Cured)

Physical Properties

Property	Value
Shore Hardness, ASTM D2240, Shore D	75-85

Typical Curing Performance

Ultrabond[®] 774 can be cured through irradiation with ultraviolet and/or visible light of sufficient intensity. To obtain full cure on surfaces exposed to air, the intensity of energy at 365 nm is particularly important. The cure rate and ultimate depth of cure will depend on light intensity, the spectral distribution of the light source, the exposure time and the light transmittance of the substrates.

Tack Free Time

Measured @ 365 nm, using medium pressure, mercury arc lamp: US 1000, at ½ inch distance: ≤ 5 seconds
By using LED9, at ¼ inch distance: ≤ 10 seconds

Typical Cured Performance

Block- Shear Strength on different specimens
Cured with US 1000, at ½ inch distance

Tested according to ASTM D4501

Specimen	Cure Conditions	Value, psi
Glass to Steel	UV-cured for 30 sec, post-cured for 24 hours at 22 °C. Tested at RT	≥ 300
Glass to Steel	UV-cured for 30 sec, post-cured for 24 hours at 22 °C. Tested hot, 150°C	≥ 300

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

Ultrabond[®] 774 is UV sensitive. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling. Product should be dispensed from applicators with black feed lines. For best performance bond surfaces should be clean and free from grease. UV cure rate is dependent on lamp intensity, distance from light source, depth of cure needed or bondline gap and light transmittance of the substrate through which the radiation must pass. For dry curing of exposed surfaces higher UV irradiance is required (100 mW/cm² minimum).

Cooling should be provided for temperature sensitive substrates such as thermoplastics. Crystalline and semi-crystalline thermoplastics should be checked for risk of stress cracking when exposed to liquid adhesive. Excess adhesive can be wiped away with organic solvent. Bonds should be allowed to cool before subjecting to any service loads.

Storage

Ultrabond[®] 774 should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Hernon® Technical Data Sheet

Ultrabond 774

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.