

## Technical Data Sheet Tuffbond<sup>®</sup> 395

April 2019

Page 1 of 1

### Product Description

**Hernon<sup>®</sup> Tuffbond<sup>®</sup> 395** is a single component, high temperature resistant, heat activated epoxy. It cures to a high-performance thermoset system with excellent adhesion properties to a wide variety of substrates. **Tuffbond<sup>®</sup> 395** will change from amber-yellow to a reddish brown upon cure.

Bonding the voice coil to the cone has been a challenge for engineers, specifically when the adhesive temperature resistance requirement is above 200°F (93°C). Two component epoxy systems have been most commonly used for this application, but limitations such as mixing ratio, cure speed, potential solidification in equipment and static mixers and the need for equipment flushing solvents have made **Tuffbond<sup>®</sup> 395** more practical.

### Product Benefits

- High temperature resistance.
- Single component (no mixing, no pot life).
- Solventless.
- Cures on demand (heat cure).
- Will not slip during cure.
- Fast setting: 1.5 minutes at 150°C bondline.
- Changes color upon cure (yellow to brown).
- Excellent adhesion to various substrates.
- Gives high shear.
- Low water absorption.
- Very rigid.
- Low density.
- No porosity upon cure.

### Typical Properties (Uncured)

Property	Value
Resin	Epoxy
Appearance	Lt yellow paste
Viscosity @ 25°C, cP	300,000 to 360,000
Specific gravity	1.21

**Tuffbond<sup>®</sup> 395** can be cured by infra-red or convection oven. Cure time will depend on the bondline temperature.

Temperature, °C (°F)	Cure Time, minutes
150 (300)	≤1.5

### Typical Cured Performance

Lap- Shear Strength, ASTM D1002  
Cured 5 minutes at 150°C

Substrate	Shear Strength, psi
GB Steel	2300 - 3300

### General Information

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

### Storage

**Tuffbond<sup>®</sup> 395** must be stored under refrigeration at a temperature of 35 to 40°F for extended shelf life. To prevent contamination of unused material, do not return any material to its original container.

### Dispensing Equipment

**Hernon<sup>®</sup>** offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon<sup>®</sup> Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING<sup>®</sup>, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.

### Curing Characteristics