

Technical Data Sheet ReAct[®] 767

April 2019

Page 1 of 2

Product Description

Hernon[®] ReAct[®] 767 is a high performance tough acrylic adhesive designed primarily for securing ceramic permanent magnet segments in motor magnet bonding applications. Used in conjunction with **Hernon[®] EF Activator 56/ Activator 47**, this structural adhesive is ideal for choke and transformer bonding, DC motor assembly, alternator and flywheel applications, tacking, unitizing, ruggedizing, sealing and shallow potting.

ReAct[®] 767 fixtures in seconds, is acrylic acid free and non-corrosive, non-flammable, and suitable for harsh environments. **ReAct[®] 767** exhibits good thermal shock, impact and peel resistance characteristics, and excellent adhesion to a wide variety of plated surfaces.

Product Benefits

Improved Reliability

- High impact and shock resistance
- Temperature resistance: -40 to 300°F (-40 to 149°C)
- Good gap filling properties.
- Excellent adhesion to a variety of surfaces.
- Consistent rate of cure from 60 to 100°F (18 to 38°C)
- Consistent bond strength
- Non-corrosive

Improved Processing

- Fast fixturing
- No pot life, no mixing
- No waste problems
- Low toxicity
- Low odor
- Thixotropic: facilitates dispensing/applying
- Non-migrating on vertical surfaces
- Increases productivity
- Requires minimal parts cleaning
- Easy clean-up

Cost Effective

- Requires minimal clamping time and tooling.
- Eliminates high energy cost needed for heat cured materials.
- Eliminates need for mechanical clips

Typical Applications

- DC motor assembly.
- Magnet bonding.
- Bonding pre-coated sheet metal.
- Bonding ferrites, plastic, and metal wear strips.
- Bonding metals with special surface treatments such as galvanized, phosphate, and dichromate surfaces.

Typical Properties (Uncured)

Property	Value
Base Resin	Modified Acrylic
Solids	100% - No Solvents
Appearance	Off-White, Translucent
Specific gravity @ 25°C	1.09
Viscosity @ 25°C, cP	50,000 – 70,000

Typical Curing Performance

ReAct[®] 767 is designed to be used with **EF[®] Activator 56** and cured at room temperature. Cure characteristics are measured by determining fixture time (handling time) and speed of cure.

Fixture Time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

Tested on steel lap-shear specimens, 2 sides primed with a minimal thin layer of **EF[®] Activator 56/ Activator 47**.

Gap, mm	Fixture Time, seconds
0	≤ 25
0.20	≤ 60

Cure Speed

The table below shows shear strength developed with time using **EF[®] Activator 47** on steel lap-shear specimens and tested according to ASTM D1002.

Cure time at RT	Shear Strength, psi
30 minutes	1000-2000
24 hours	1500-2500
48 hours	1800-2800

Typical Properties (Cured)

Method	Property	Value
ASTM D2240	Durometer Hardness, Shore D	55-65
ASTM 6110	Energy, G/B Aluminum, Cured at RT for 24 hours, Joules	≥ 15
ASTM 6110	Energy, G/B Steel, Cured at RT for 24 hours, Joules	≥ 15

Typical Cured Performance

Shear Strength

Tested on Steel lap-shear specimens with 1 side primed with a minimal thin layer of **EF® Activator 56** and tested according to ASTM D1002.

Cured Time at RT	Shear Strength, psi
30 minutes	1000-1500
24 hours	1500-2500

Typical Environmental Resistance

Shear Strength, steel lap-shear specimens, 1 side primed with **EF® Activator 56**, cured for 48 hours at 22°C and tested according to ASTM D1002.

Heat Aging

Aged for 72 hours at temperature indicated and tested at 22°C.

Temperature	Shear Strength, N/mm ² (psi)
90°C	≥ 20.7 (3000)
120°C	≥ 17.2 (2500)
150°C	≥ 15.2 (2000)

Chemical/Solvent Resistance

Aged under conditions indicated and tested at 22°C.

Chemical/Solvent	Temp (°C)	% of Initial Strength	
		720 hours	1440 hours
Air Reference	87	100	100
Water Glycol 50/50	87	36	23
Gasoline	22	44	18
Motor Oil	87	100	100

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

1. For best performance bond surfaces should be clean and free from grease.
2. To ensure a fast and reliable cure, **EF® Activator 56** or **EF® Activator 47** should be applied as a minimal thin layer to one of the bond surfaces and the adhesive to the other surface. **EF® Activator 56** Adhesive to primer ratio is approximately 10:1. For **EF 47** the ratio would be 15:1 up to 20:1 adhesive/primer ratio.

Parts should be assembled within 15 minutes.

3. The recommended bond-line gap is ≤ 0.1mm. Where bond gaps are large (over 0.1mm), or surfaces are porous, **EF® Activator 56/ Activator 47** should be applied to both surfaces. Parts should be assembled immediately (within 1 minute).
4. Excess adhesive can be wiped away with organic solvent.
5. Bond should be held clamped until adhesive has fixtured.
6. Product should be allowed to develop full strength before subjecting to any service loads (typically 24 to 72 hours after assembly, depending on bond gap, materials and ambient conditions).

Storage

ReAct® 767 should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.