

Technical Data Sheet Mine Sealer 2007

December 2009

Page 1 of 1

Product Description

Hernon[®] Mine Sealer 2007 is an ultraviolet curable adhesive sealant formulated to provide a rapid and deep curing ability when exposed to high intensity ultraviolet energy.

Typical Properties

Property	Value
Resin	Urethane acrylate
Appearance	Clear liquid
Viscosity @ 25°C, cP	125,000 to 200,000
Specific gravity	1.10
Flash point	See MSDS

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Mine Sealer 2007 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 82°F (8°C to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon[®] Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO 9001 Quality Standard.