

Technical Data Sheet Tuffbond[®] 302

February 2014

Page 1 of 2

Product Description

Hernon[®] Tuffbond[®] 302 is a modified epoxy adhesive that provides a very fast room temperature cure. **Tuffbond[®] 302** exhibits very good moisture chemical and heat resistance. This very fast cure epoxy adhesive is specially formulated for rapid in-line assembly of loud speakers. **Tuffbond[®] 302** is also recommended for bonding metals, wood, ceramics, etc., and can be used for potting and encapsulation of electrical and electronic components.

Typical Applications

- Bonding voice coil to cone
- Bonding pole piece to magnet
- Bonding alnico magnet to base
- Rapid curing structural and electrical repair kit
- Rapid curing laminates and "gel" coats
- Potting electronic boards
- Encapsulating electrical and electronic components

Product Benefits

- Fast cure at room temperature (about 5 minutes)
- Low shrinkage
- 100% reactive, non-solvent system
- Easy mixing ratio of resin and hardener
- No fuming on gelation

Typical Properties (Uncured)

Property	Part A	Part B
Base	Epoxy	Amine
Appearance	White	Clear - Light amber
Viscosity at 25°C, cP	50,000 to 60,000	50,000 to 60,000
Mix Ratio by Weight	1	1
Specific Gravity	1.18	1.13
Flash Point	See MSDS	See MSDS

Typical Properties (Cured)

Property	Value
Working Life at 22°C (20g), minutes	≤ 5
Durometer Hardness, Shore D	85 - 90
Glass Transition Temperature, (T _g) °C	52
Operating Temp., °C	-54 to 85

Typical Cured Performance

Room Temperature Cure

Shear Strength on Aluminum lap-shear specimens tested according to ASTM D1002.

Cure Time at 22°C	Shear Strength
24 Hours	≥ 1500 psi
30 Days	≥ 2000 psi

Chemical/Solvent Resistance

Shear Strength on Aluminum lap-shear specimens tested according to ASTM D1002. Cured for 24 hours at 22°C. Immersed in Chemical/Solvent for 30 days at 22°C.

Chemical/Solvent	% Strength Retention
10 % Sodium Chloride	83
Distilled Water	81
5% Acetic Acid	79
Petrohol 99	100
Hydrocarbon Test Fluid	94
Ethylene Glycol	100
Hydraulic Oil	99

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Tuffbond® 302 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 85°F (8°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO 9001 Quality Standard.